

# STEF SEALER

## **1-PRODUCT DESCRIPTION**

A coating based on a 100% acrylic emulsion formulated for porous surfaces. The finish is low sheen and ready to sand. .

## **2-USES**

The product will yield excellent results on new gypsum board and cement walls. It is recommended for interior use on all surfaces except metal or new wood

## **3-DIRECTIONS FOR USE**

Stir well before using. Do not thin this product. Apply at temperature between 10 - 30°C using a brush, roller and spray equipment. One coat will usually suffice to obtain uniform results. Clean tools using warm, soapy water

## **4-SURFACE PREPARATION**

Surfaces to be painted must clean, dry and free from all contaminants. Repair cracks and cover nail heads with the appropriate mastic or compound.

## **5- LIMITATIONS AND RESTRICTIONS:**

Avoid painting if the relative humidity exceeds 85%. Wash the walls and moldings to remove any dust and dirt. Clean oil and grease on the walls of kitchens and bathrooms which are often deposited thin films of grease. Remove glue residue from the wallpaper to ensure a uniform finish. Make sure the primer and the paint finish from the same manufacturer to avoid loss of adhesion.

## **6-COVERAGE**

Based on theoretical coverage i.e. no losses. Actual coverage may vary according to application method, texture & porosity of substrate.

## **7-TECHNICAL DATA**

Appearance: White, beige

Gloss (60°) : 8% ± 2

Viscosity: 98 ± 2 KU

PH (100% ): 8 - 9

Odor: Mild

Density: 1.277 ± 0.03

Composition:

Vehicle type: Acrylic Latex  
emulsion

Thinner: Water

Binder: Vinyl acrylic latex

Volatile Organic Compounds:

VOC < 50g/L

Weight per Gallon:

10.75 ± .25 lbs /gal

Solids by weight :48± 1%

Solids by volume :  $33 \pm 1\%$   
Recommended Dry Film  
Thickness (DFT): 1.0 mils or  
25.0 microns, per coat (Two  
coats are recommended).  
Wet Film to Achieve (WFT):  
3.03 – 4.54 mil  
Theoretical coverage :  
529 sq ft/gal, 13.0 m<sup>2</sup>  
/L, at 1 mil  
(25 microns) DFT  
Practical coverage:  
11.04 m<sup>2</sup>/litre mil 450 pi<sup>2</sup>/gal-mil  
Dry times: Drying time may be  
longer depending on humidity,  
temperature variation, texture  
and surface porosity.  
Tack free: 1 hour  
Recoat: 2-3 hours  
Shelf life: 01 year, in unopened  
containers properly stored in a  
cool dry area.  
Packaging:  
Sizes: : 4 L : 17 L

The application instructions and performance characteristics are based on information we believe to be reliable. They are offered to the best of our knowledge, but without guarantee, as conditions and methods of use of our products are beyond our control.



Bsous, Main Road, Aley Mount Lebanon

Version : 200 858

Page 2 o 2

[info@stefleb.com](mailto:info@stefleb.com)

<http://Stefmiddleeast.com>