

STEF-TEK ROLL

(*Liquid membrane – Water-Barrier and Air-Barrier to waterproof the substrate*)

4- Installation

1- Product description

Stef-Tek Roll is a flexible, ready-to-use coating that is just a single component, and acts continuously as an air and water barrier. It is a 100% acrylic product that is easy to apply. The product is designed to be applied with a brush or roll on wood, Aspenite (OSB) or plywood, concrete or gypsum to increase resistance to a building's climate. **Stef-Tek Roll** will remain elastic and flexible even in cold temperatures.

Two layers are required for waterproofing of the surface. The minimum thickness of **Stef-Tek Roll** is 1/16 "(1.6 mm) wet when applied to the total of the two layers.

Stef-Tek Roll should not be used for joints, use **StefTek** for joints.

| Characteristics | Advantages |
|----------------------|---|
| Resistance to water. | Prevents infiltration. |
| Resistance to vapor. | Moisture is not trapped in the walls. |
| Resistance to air. | Reduces condensation and heating costs. |
| No joint. | Uniform membrane. |

2- Covered surface area

An 17L container (20 kilos) of **Stef-Tek Roll** covers approximately 50 m² for 1 coat.

3- Product properties

Stef-Tek Roll is an easy product to use.

Stef-Tek Roll can be used as an elastomeric finishing coating. The product is specially formulated to resist the accumulation of dust. For a long-term finish the use of **Texnov Met-30** sealant is advised horizontal surfaces.

Temporary protection: While the entire application of the **Stef-Tek Roll** membrane, insulation panels, the flashing membranes, flashings, the base coat layer, the finishing and sealing layer, is not completed, the wall or floor must be protected against rain, weather and possible other damage.

Surface preparation: The surface of the substrate on which the protective **Stef-Tek Roll** membrane is applied must be dry, clean, free from dust, wax, grease, oil, rust, or any other dirt can that lessen adhesion before application.

Product application: Mix the product with a drill that has a corrosion-resistant bit before use. Care should be taken to not allow air to enter the product during mixing. No additives and no water should be added to the product.

For some projects, **Stef-Tek Roll** can be covered directly with finishing plaster.

During installation of the product: the air and ambient temperature must be between 5°C (41°F) and 40°C (104°F) and must remain so for a minimum of 24 h.

Drying: The drying time of **Stef-Tek Roll** depends on the air temperature, wind and relative humidity. In normal drying conditions (20°C and 50% RH), the surface is dry to the touch after approximately 2 hours.

Cleaning: Clean the tools with water while the **StefTek Roll** mixture is still wet.

5- Storing the product

Stef-Tek Roll must be stored in its original container at a temperature of 5°C (41°F) to 40°C (104°F) in a dry place protected from the sun's rays. Keep away from frost. The service life of the product is 1 year.

STEF-TEK ROLL

(Liquid membrane – Water-Barrier and Air-Barrier to waterproof the substrate)

6- Transportation conditions Regulated shipping

name: not applicable.

TDG category: Not regulated. **Note:** This product requires no special measures for international transport.

| Mixture Properties | |
|---|------------|
| Solid | 70 % |
| pH | 8.7 |
| Viscosity Brookfield DV2T Spindle H6 (10 rpm) | 30 000 cps |
| Density at 20°C (g/cm ³) | 1.25 |

| Performance of <i>Stef-Tek RLX</i> ^{*4} | |
|--|--|
| Test and method requirement | Results |
| Transmission of water vapor CCMC 5.3.4 / ASTM E96 ^{*1-2} | 1150 ng/Pa·s·m ² (20.1 Perms) |
| Adhesion ^{*3} CCMC 5.3.3 / ASTM D1623 ≥0.3 MPa | 0.40 MPa (Aspenite and EPS) 0.43 MPa (plywood) 0.48 MPa (concrete) |
| Water absorption coefficient 72 h CCMC 5.4.4 /ISO 15148 ≤0.004 kg / (m ² · s ^{1/2}) | 0.0005 kg / (m ² · s ^{1/2}) |
| Resistance to water transmission ^{*4} CCMC 5.4.7 ≤0.00020 g / m ² · s | 0.00016 g / m ² · s |
| Nail lift resistance CCMC 5.4.8 No adverse effects | Successful |

* 1 According to ASHRAE 2009, a vapor permeable product should have ≥10 perms and a vapor barrier should have ≤0.1 perms.

* 2 Test carried out according to ASTM E96-procedure B (water), at STEF's laboratory, no substrate, film thickness 1.6 mm.

* 3 Measured after gasket elongation and cyclical environmental conditions induced.

* 4 Internal result obtained in the laboratory of STEF coatings according to the ASTM standard in force and to the best of our knowledge.